技术参数表

Technology Data Sheet

名称Name	PET光银5c水胶-60g格底			50mic PET sliver Acrylic-60gsm white glassine
面材Face wood	38um光银PET			38mic PET sliver
胶水Glue	水性型压敏胶			Acrylic
底材Underwood	60g白格拉辛硅纸			60gsm white glassine
技术指标 Technical index	参数值 Argument value	单位 Unit	方法 Method	产品说明 Description of products
面材Face Wood				材料特性Material Behavior
克重 Gram weight	52±2	g/m2	GB/T 451.2-2002	材料热塑性聚酯膜经过真空镀铝而成,材料挺度大,耐温性好,适用于平张印刷、胶版印刷、柔版印刷等多类别印刷工艺(材料无涂层,印刷都不得对印刷面进行破坏)。 The material thermoplastic polyester film is made of vacuum aluminum plating, the material stiffness is large, the temperature resistance is good, suitable for flat printing, offset printing, flexographic printing and other types of printing process (the material is not coated, printing must not destroy the printing surface).
厚度 Thickness	37±2	um	GB/T 451.3-2003	
涂层 Coated	No	Yes/No	试剂擦拭 Reagent wiping	
胶粘剂Adhesive				材料特性Material Behavior
环形初粘 Looptack on SS	>900	gf/Inch	FTM-9	材料为丙烯酸水性压敏胶,是环保型材料,具有良好粘性及耐候性,可应用于多种材质的粘贴,材料不耐水并且不可接触其他化学试剂。 The material is acrylic water-based pressure-sensitive adhesive, which is an environmentally friendly material with good viscosity and weather resistance. It can be used for pasting various materials. The material is not water-resistant and can not contact other chemical reagents.
剥离强度 90°Peel on SS	>500	gf/Inch	FTM-2	
持粘力 Shear	>12	Hr	FTM-8	
底材 Liner				材料特性Material Behavior
成品克重 Gram weight	58±3	g/m2	GB/T 451.2-2002	材料为高紧致度超压纸张表面带有离型涂层,具有良好平整性、抗拉强度及透明,适合应用于不干胶产品卷筒印刷、模切及后道自动贴标等应用。 The material is high compactness overpressure paper with release coating on the surface, with good flatness, tensile strength and transparency, suitable for roll printing, die-cutting and automatic labeling of self-adhesive products.
厚度 Thickness	50±3	um	GB/T 451.3-2003	
产品储存及使用环境Product storage and use environment				产品应用Product application
个月。超过有效期的产品,经检验合格仍可使用。				广泛应用于电子、家电、汽车、化工等行业。 Widely used in electronics, home appliances, automobiles, chemical and other industries.

特别说明Special note

- 1.盈之泰所有有关材料的说明、技术信息及使用推荐是基于我们认为可信的测试结果,但不构成一种担保。
- 2.由于产品的使用条件和加工条件不同,在使用之前请测试,避免未知的风险。
- 3.技术文件以盈之泰现行条款为准,盈之泰公司保留最终解释权。
- 1. All descriptions of materials, technical information and recommendations for use by Yingzhitai are based on test results that we believe to be credible, but do not constitute a warranty.
- 2. Due to the different use conditions and processing conditions of the product, please test before use to avoid unknown risks.
- 3. The technical documents shall be subject to the current terms of Yingzhitai, and Yingzhitai reserves the right of final interpretation.